

Setseal B

Elastomeric acrylic cement modified waterproof coating



Description

Setseal B is a two component; elastomeric polymer modified cementitious waterproof coating suitable for internal and external applications.

Setseal B provides a hardwearing, seamless, waterproof membrane for potable water retaining structures, tanks, basements, foundations and culverts.

Setseal B shows excellent crack accommodation and is suitable for use on concrete.

Applications

- ▲ Waterproofing of water retaining structures and reservoirs.
- ▲ Waterproofing of basements, roof, and foundations.
- ▲ Waterproofing of bathrooms and wet areas.
- ▲ Protection of concrete substrates and masonry against carbon dioxide, chloride ions, water and de-icing salts.

Advantages

- ▲ Non-toxic, approved for use in contact with potable water.
- ▲ Elastomeric, can accommodate static and dynamic cracks.
- ▲ Fungus and mould resistant.
- ▲ Able to withstand high positive and negative water pressures.
- ▲ Excellent bond to porous and non-porous surfaces.
- ▲ Breathable.
- ▲ Durable, excellent protection against carbon dioxide, chloride ions and water.
- ▲ Cost effective, quick and easy brush, roll or spray application.
- ▲ Suitable for internal and external applications.

Standards

- ▲ Setseal B complies with BS 6920 for using in contact with potable water.
- ▲ Setseal B complies with the requirements of EN 1504-2 Surface Protection System Principle 1.3, 2.2 and 8.2.

Technical Properties @ 25°C:

Mixed density:	1.85 g/cm ³
Working time:	45 min
Colour:	Grey or white
Resistance to water pressure (2 mm coating): DIN 1048	> 70 m positive (7 bars) > 50 m negative (5 bars)
Static crack accommodation:	> 0.8 mm
Mixing ratio:	5.1 kg liquid polymer with 17.9 kg powder
VOC:	< 10 g/ltr (powder) < 20 g/ltr (liquid)
Minimum application temperature:	5°C
Bond Strength on normal concrete: ASTM D4541	≥ 1.5 MPa @ 28 days
Bond Strength on gypsum boards: ASTM D4541	Gypsum failure
Tensile strength: BS 6319, Part 7 (mortar consistency)	≥ 2 MPa @ 28 days (dry cure)
Flexural strength: (mortar consistency) ASTM C348	> 8 MPa (dry cure)
Compressive strength: ASTM C109 (mortar consistency)	≥ 15 MPa (dry cure)
Elongation at break: ASTM D412(without reinforcement @ thicknesses > 2 mm)	≥ 15% @ low speed rate ≥ 5% @ high speed rate

Note: These results were achieved using 2mm thickness.



Setseal B

Method of Use

Substrate Preparation

The surfaces to be coated should be clean, sound, and free from contamination. Remove any traces of curing compound, laitance, organic growth or any other loose materials.

This is best obtained by using high pressure water or light grit blasting. Substrate containing honey combing, damaged or deteriorated concrete should be repaired using suitable repair mortars from DCP repair systems before coating.

Priming

No special primer is required, but substrate should be pre-soaked with clean water prior to application of Setseal B.

Mixing

To ensure proper mixing, a mechanically powered mixer or drill fitted with suitable paddle should be used. Add the liquid component of Setseal B to a clean container.

The powder component is then added slowly to the liquid while mixing continuously with low speed mixer/drill (400 - 600 rpm). Mixing time should be continued for 3 minutes until a uniform consistency is obtained.

Application

Setseal B can be applied by brush, roller, trowel, or spray machines. The mixed material should be brushed/rolled well into the substrate. Strike off with brush or roller in one direction.

Care must be taken not to spread the materials too thin. The first coat should be applied at a wet film thickness of 1 mm. When the material begins to drag, do not add any water, but dampen the surface again.

A minimum of 3 - 5 hours, depending on the prevailing ambient temperature, should be given for the first coat to cure before applying the second coat. If the first coat is left exposed for a long period of time, it is recommended to wash the surface with water before applying the second coat, in order to ensure a dust free surface.

For brush or roller application, the second coat should be applied in a perpendicular direction to the previous layer to ensure good bond and coverage.

Performance characteristics	EN 1504-2 requirements	Measured value
Permeability to CO ₂ : EN 1062-6	S _D > 50 m	S _D > 115 m
Water vapour permeability: ISO 7783-2	Class I: S _D < 5 m Class II: 5 ≤ S _D ≤ 50 m Class III: S _D > 50 m	S _D ≤ 0.5 m (Permeable to water vapour)
Capillary water absorption: EN 1062-3	< 0.1 kg/m ² .h ^{0.5}	≤ 0.025 kg/m ² .h ^{0.5}
Adhesion strength: EN 1542	Without trafficking ≥ 0.8 MPa With trafficking ≥ 1.5 MPa	≥ 1.5 MPa (Flexible systems with trafficking)

To achieve a smooth finish, it is recommended to finish the surface with a trowel immediately after brushing the second coat. The total dry film thickness for both coats should be 2 mm.

Remarks

- ▲ Setseal B should not be applied to frozen substrates or if ambient temperature is below 5°C or expected to fall below 5°C.
- ▲ The area must not be exposed to moving water during application.
- ▲ Setseal B can be submerged with water after 5 – 7 days of application depending on ambient temperatures and relative humidity.
- ▲ Where cementitious plaster is to be applied over Setseal B, a mix of sand, cement and Cempatch SBR should be sprayed over Setseal B as key. Addition rate of Cempatch SBR should be 10 litre/bag of cement.

Cleaning

All tools should be cleaned immediately after finishing using clean water. Hardened materials should be cleaned mechanically.

Packaging

Setseal B is available as 23 kg packs.



Setseal B

Coverage

Approximately 12-13 m² per 23 kg for one coat @ 1 mm thickness, depending on the condition of the surface and method of application.

Storage

Setseal B has a shelf life of 12 months from date of manufacture if stored at temperatures between 5°C and 35°C.

If these conditions are exceeded, DCP Technical Department should be contacted for advise.

Cautions

Health and Safety

As Setseal B contains Portland cement, Setseal B may cause irritation to skin or eyes.

In case of accidental contact with eyes, immediately flush with plenty of water for at least 10 minutes and seek medical advise if necessary.

For further information refer to the Material Safety Data Sheet.

Fire

Setseal B is nonflammable.

More from Don Construction Products

A wide range of construction chemical products are manufactured by DCP which include:

- ▲ Concrete admixtures.
- ▲ Surface treatments
- ▲ Grouts and anchors.
- ▲ Concrete repair.
- ▲ Flooring systems.
- ▲ Protective coatings.
- ▲ Sealants.
- ▲ Waterproofing.
- ▲ Adhesives.
- ▲ Tile adhesives and grouts.
- ▲ Building products.
- ▲ Structural strengthening.

Setseal B



Note:

We endeavour to ensure that any information, advice or recommendation we may give in product literature is accurate and correct. However, because we have no control over where and how products are applied, we cannot accept any liability arising from the use of the products.

-  expertise
-  quality
-  full range

www.dcp-int.com

08-0009-B-2021